

BTE

2

OFFICE OF NAVAL RESEARCH

Research Contract N00014-87-K-0014

R&T Code 413a001

Technical Report No. 16

THERMODYNAMICALLY STABLE CONDUCTING FILMS
OF INTERMETALLIC PtGa_2 ON GALLIUM ARSENIDE

by

Larry P. Sadwick,* Kang L. Wang,*
David K. Shuh,[†] Young K. Kim,[†] and R. Stanley Williams[†]

To be published

in

Proc. Mat. Res. Soc. Spring Symp. in San Diego, 1989

University of California, Los Angeles

[†]Department of Chemistry & Biochemistry and Solid State Science Center
Los Angeles, CA 90024-1569

and

*Department of Chemical Engineering
Los Angeles, CA 90024-1594

July 1, 1989

SDTIC
ELECTE
JUN 22 1989
H

Reproduction in whole or part is permitted for any purpose of the United States Government.

This document has been approved for public release and sale;
its distribution is unlimited

89 6 21 026

AD-A210 077

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE

REPORT DOCUMENTATION PAGE

1a REPORT SECURITY CLASSIFICATION UNCLASSIFIED			1b RESTRICTIVE MARKINGS N/A	
2a SECURITY CLASSIFICATION AUTHORITY N/A			3. DISTRIBUTION / AVAILABILITY OF REPORT Approved for public release; distribution unlimited	
2b DECLASSIFICATION / DOWNGRADING SCHEDULE N/A				
4. PERFORMING ORGANIZATION REPORT NUMBER(S) N/A			5. MONITORING ORGANIZATION REPORT NUMBER(S)	
6a. NAME OF PERFORMING ORGANIZATION The Regents of the University of California		6b OFFICE SYMBOL (If applicable)		7a NAME OF MONITORING ORGANIZATION 1) ONR Pasadena - Administrative 2) ONR Alexandria - Technical
6c ADDRESS (City, State, and ZIP Code) Office of Contracts & Grants Administration U C L A, 405 Hilgard Avenue Los Angeles, CA 90024			7b ADDRESS (City, State, and ZIP Code) 1) 1030 E. Green Street, Pasadena, CA 91106 2) 800 N. Quincy St., Arlington, VA 22217-5000	
8a. NAME OF FUNDING / SPONSORING ORGANIZATION Office of Naval Research		8b OFFICE SYMBOL (If applicable) ONR		9 PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-87-K-0014
8c ADDRESS (City, State, and ZIP Code) 800 N. Quincy Street, 614A:DHP Arlington, VA 22217-5000			10 SOURCE OF FUNDING NUMBERS	
			PROGRAM ELEMENT NO.	PROJECT NO.
			TASK NO.	WORK UNIT ACCESSION NO.
11 TITLE (Include Security Classification) UNCLASSIFIED: Thermodynamically stable conducting films of intermetallic $PtGa_2$ on gallium arsenide				
12 PERSONAL AUTHOR(S) Larry P. Sadwick, Kang L. Wang, David K. Shuh, Young K. Kim and R. Stanley Williams				
13a TYPE OF REPORT Tech. Rept. #16		13b TIME COVERED FROM 1988 TO 1989		14 DATE OF REPORT (Year, Month, Day) 20 June 1989
15 PAGE COUNT 6				
16 SUPPLEMENTARY NOTATION				
17. COSATI CODES			18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB-GROUP	epitaxial films - ultra-high vacuum - chemical stability - compound semiconductors - contact degradation - Schottky barrier - Fermi level pinning. (STES) ←	
19. ABSTRACT (Continue on reverse if necessary and identify by block number) The first epitaxial platinum gallium two ($PtGa_2$) films have been grown on gallium arsenide (GaAs)(100) by co-evaporation of the elements under ultra-high vacuum conditions. An electron-beam evaporator and a Knudsen cell were used to produce the platinum and gallium beams, respectively. The resulting films and bulk $PtGa_2$ have been characterized by x-ray diffraction, Auger electron spectroscopy, and x-ray photoelectron spectroscopy. The data confirm the $PtGa_2$ stoichiometry and crystal structure of the films, and demonstrate their chemical stability on GaAs(100). This study supports the contention that $PtGa_2$ can be a suitable, temperature-stable contact material on GaAs substrates.				
20 DISTRIBUTION / AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION UNCLASSIFIED	
22a NAME OF RESPONSIBLE INDIVIDUAL R. Stanley Williams			22b TELEPHONE (Include Area Code) (213) 825-8818	22c OFFICE SYMBOL UCLA

THERMODYNAMICALLY STABLE CONDUCTING FILMS OF INTERMETALLIC PtGa_2 ON GALLIUM ARSENIDE

Larry P. Sadwick*, Kang L. Wang*, David K. Shuh**, Young K. Kim**, and R. Stanley Williams**

*University of California Los Angeles Department of Electrical Engineering Device Research Laboratory, 7732 Boelter Hall, Los Angeles, CA 90024

**University of California Los Angeles Department of Chemistry and Biochemistry and Solid Science Center, 2080 Young Hall, Los Angeles, CA 90024.

ABSTRACT

The first epitaxial platinum gallium two (PtGa_2) films have been grown on gallium arsenide (GaAs) (100) by co-evaporation of the elements under ultra-high vacuum conditions. An electron beam evaporator and a Knudsen cell were used to produce the platinum and gallium beams, respectively. The resulting films and bulk PtGa_2 have been characterized by x-ray diffraction, Auger electron spectroscopy, and x-ray photoelectron spectroscopy. The data confirm the PtGa_2 stoichiometry and crystal structure of the films, and demonstrate their chemical stability on GaAs (100). This study supports the contention that PtGa_2 can be a suitable, temperature stable contact material on GaAs substrates.

Introduction

The chemistry of metal-semiconductor interfaces ultimately controls the nature of Schottky barrier or Ohmic contact formation [1]. Contact formation on elemental semiconductors is relatively straightforward because of the simplicity of binary phase systems, which have a limited number of reaction products. Transition to compound semiconductor technology has encountered additional difficulty because ternary phase diagrams are significantly more complex and rarely well characterized [2].

In order to employ GaAs based electronic devices for both high reliability and harsh environment applications, chemically stable contacts must be formed at the metal-semiconductor interface. Conventional methods to alleviate temperature induced contact degradation usually involve passivation or interdiffusion barriers [3].

A simple solution to the degradation problem would be the use of an intermetallic compound that is thermodynamically stable to the GaAs surface and that also possesses suitable electronic transport properties [4]. Therefore, the intention of this study was to select and investigate an intermetallic contact on GaAs system chosen from a known ternary phase diagram. The intermetallic compound should exhibit a thermodynamically stable tieline to the GaAs semiconductor. A further consideration is that the intermetallic should be compatible with existing molecular beam epitaxy (MBE) techniques.

On the basis of the Pt-Ga-As ternary phase diagram, as experimentally elucidated by Tsai et. al. [5] and illustrated in Fig. 1, PtGa_2 was selected as a candidate for thin film growth on GaAs (100). The existence of the pseudobinary tieline between PtGa_2 and GaAs implies that the two bulk compounds do not react with each other in a closed system. PtGa_2 is a thermodynamically favored reaction product of the Pt-Ga-As system. Depositing an elemental Pt film on GaAs and then annealing will induce chemical reactions that yield intermetallic compounds of Pt with both Ga and As, accompanied by the subsequent degradation of the interface [5]. Since

PtGa₂ is a potential product of such a reaction, it will be much more stable in contact with GaAs than Pt.

Advanced device considerations require that the contacts on GaAs be stable to temperatures in excess of 800°C. The PtGa₂ films are stable up to 450°C in air during long-time anneals; further work involving capping or other equivalent procedures is required to determine if stability above 800°C can be achieved.




Figure 1. Solidus portion of Pt-Ga-As ternary phase diagram at 25 ° C.

Growth

The PtGa₂ films were grown in a MBE chamber with a base pressure of 2×10^{-10} torr and a deposition pressure of 4×10^{-9} torr. The two inch GaAs wafers were introduced via a cryopumped load lock system and mounted on a modified manipulator equipped with radiative heating elements. The samples were cleaned by heating to a temperature of 550°C under an arsenic overpressure obtained from a Knudsen cell to prevent surface decomposition of the GaAs. The platinum was evaporated using a Varian 3 KW electron beam evaporator and the gallium was obtained from a Knudsen cell constructed of a pyrolytic boron nitride (PBN) crucible with a tantalum heating element. The fluxes of platinum and gallium were initially tuned to the proper stoichiometry. PtGa₂ can be visually identified by its characteristic golden color, as PtGa₂ is the only Pt-Ga phase that has a band structure similar to that of elemental gold [5,6]. The flux rate from the gallium source was stabilized by temperature control circuits that ensured a constant flux rate for each source power setting. Subsequent depositions have been controlled with a Leybold-Inficon IC-6000 crystal monitor system. To obtain single phase PtGa₂ films, the flux ratio of gallium to platinum was adjusted to slightly greater than 2 to 1. Co-evaporation of the PtGa₂ proceeded with the sample held at substrate temperatures ranging from near room temperature to over 500°C at an epilayer growth of approximately 5 microns/hour.



For	<input checked="" type="checkbox"/>
by	<input type="checkbox"/>
ty Codes	<input type="checkbox"/>
and/or	
cial	

A-1

Structural and Chemical Characterization

Powder x-ray diffractometry (XRD) patterns of the films were taken on a Philips diffractometer utilizing a Crystal Logic interface to a DEC VAX 11/750 mainframe computer. Diffraction patterns were obtained by accumulation of data for periods of time upwards of twelve hours to achieve an adequate signal to noise ratio. The thin PtGa₂ films were annealed in a tube furnace under both nitrogen and air ambients. The film composition and crystallite orientation was subsequently determined by XRD to ascertain the temperature behavior of the epitaxially deposited material. Auger electron spectroscopy (AES) and x-ray photoelectron spectroscopy (XPS) of the PtGa₂ thin films and bulk material were performed in a KRATOS XSAM 800 spectrometer that was equipped with a sample treatment chamber (STC), scanning electron microscope (SEM) and ES300 electron spectrometer. In addition, the sample analysis chamber was equipped with a manipulator capable of heating samples up to 450°C while in the analysis position. The base pressure during sample analysis was 2×10^{-10} torr. The samples were subjected to short, low current, rastered 3 KeV ion bombardments until AES revealed no carbon or oxygen contaminants. The samples were then annealed at various temperatures (maximum 450°C) after which AES and XPS data were collected. The XPS data were collected using an aluminum K α excitation source.

Results and Discussion

The resultant films were specular under both optical and SEM examination and golden in appearance. The films were determined to be PtGa₂ by the analytical techniques described above. The range of composition of PtGa₂ is very narrow, unlike many other intermetallic compounds which have a wide acceptance range of compositions. Figure 2a shows a powder XRD pattern of an oriented PtGa₂ (110) film (as seen by the 220 reflection at 43.3°) which was grown on a GaAs (100) substrate at room temperature. Figure 2b shows the XRD pattern obtained after the sample had been annealed at 200°C in a conventional furnace tube. The PtGa₂ peaks are virtually unchanged after subsequent annealing to 400°C as shown in figure 2c. The XRD patterns of figures 2a through c consists of peaks solely due to PtGa₂ and GaAs. The peaks at 26.0°, 43.3° and 51.0° are the (111), (220) and (311) reflections of PtGa₂, respectively. The peak at 66° is the (400) reflection from the (100) GaAs substrate. The XRD pattern showed no observable change from room temperature to annealing temperatures on the order of 450°C. Above 450°C, a small peak around 42.5° was detected. This peak is most probably due to the formation of a Pt₃Ga₇ phase which coexists with the PtGa₂ phase. At temperatures above 550°C, a sharp decrease in the intensity of the PtGa₂ peaks occurred in conjunction with the appearance of peaks due to PtGa and, most likely, PtAs₂.

The electron spectroscopies clearly indicate that the thin film samples have the same stoichiometry and valence band structure as that of a bulk PtGa₂ sample. This further served as a verification of the identity and uniformity of the thin PtGa₂ films. The stoichiometries were determined by comparisons of the relative peak to peak response of the AES and by the relative peak areas of the XPS data between the thin film samples and a bulk standard. Figure 3 shows the AES signals from a thin film of PtGa₂ on GaAs. The electron distribution curves (EDC) determined from the core levels and valence bands are presented in Figs. 4 and 5. In all cases, the thin films produced results that were indistinguishable from the bulk sample.




Figure 2. XRD pattern of PtGa₂ on (100) GaAs. 2a: room temperature, 2b: annealed at 200°C, 2c: annealed at 400°C. All peaks except the (400) GaAs at 66° correspond to PtGa₂.

Conclusions

The successful growth on GaAs (100) of an intentionally designed stable intermetallic thin film that is similar to silicides currently employed in standard silicon processing has been demonstrated. The PtGa₂ films are chemically stable on GaAs (100) up to 450°C. PtGa₂ shows promise as a suitable contacting material for high reliability applications.

The formation of thermochemically stable PtGa₂ epilayers on GaAs will provide an interesting system for the investigation into the nature of Schottky barrier formation and subsequent Fermi level pinning at the interface. We believe that chemically stable PtGa₂ intermetallics should eliminate many of the possible chemical factors which influence or effect the phenomenon of Fermi level pinning.

Work in progress to further understand the PtGa family-GaAs system includes temperature-dependent TEM, transport measurements and the characterization of various intermediate Pt-Ga phases grown by MBE [7].




Figure 3. AES spectra of PtGa₂ film. The only observable peaks are due to Ga and Pt. The calculated ratio is Ga:Pt 2:1.




Figure 4. XPS binding energy spectra of PtGa₂ film.




Figure 5. Valence band of PtGa₂ film which is identical to bulk PtGa₂.

Acknowledgements

This work was supported by the office of Naval Research/SDIO, the State of California MICRO program and Hughes Aircraft. RSW received further support from the Alfred P. Sloan and the Camille and Henry Dreyfuss Foundations.

References

1. L.J. Brillson, J. Phys. Chem. Solids **44**, 703 (1983).
2. C.T. Tsai and R.S. Williams, J. Mater. Res. **1**, 820 (1986).
3. V.L. Rideout, Solid State Electronics **18**, 541 (1975).
4. J.R. Lince and R.S. Williams, J. Mater. Res. **1**, 537 (1986).
5. C.T. Tsai and R.S. Williams, unpublished.
6. S. Kim, L. Hsu and R.S. Williams, Phys. Rev. B **36**, 3099, (1987).
7. L.P. Sadwick, K.L. Wang, Y.K. Kim, D.K. Shuh and R.S. Williams, unpublished.

Dr. J. Balbach-Scheller Chemistry & Chem. Engrg. Calif. Inst. of Technology Pasadena, CA 91125	Dr. John Eyley Department of Chemistry University of Florida Gainesville, FL 32611	Dr. Mark Johnson Department of Chemistry Yale University New Haven, CT 06511	Dr. R.E. Smalley Department of Chemistry Rice University, Box 1892 Houston, TX 77251	Dr. N. Winograd Chemistry Dept. Case Western Res. Univ. University Park, PA 16802	Office of Naval Research Chemistry Div., Code 1113 800 N. Quincy Avenue Arlington, VA 22217-5000 Chief of Naval Research Spec. Assistant, Marine Corps Code 00MC 800 N. Quincy Street Arlington, VA 22217-5000
Dr. Paul G. Barbara Department of Chemistry University of Minnesota Minneapolis, MN 55455-0431	Dr. James F. Garvey Department of Chemistry State University of New York Buffalo, NY 14214	Dr. Sylvia M. Johnson SRJ International 333 Ravenswood Avenue Menlo Park, CA 94025	Dr. G.A. Somorjai Chemistry Dept. University of California Berkeley, CA 94720	Dr. A. Wold Chemistry Dept. Brown University Providence, RI 02912	Commanding Officer Naval Weapons Support Center Attn: Dr. Bernard E. Douda Oran, IN 47522-5050
Dr. Duncan W. Brown Adv. Technology Mtls., Inc. 520-B Dabury Road New Milford, CT 06776	Dr. T.F. George Chemistry/Physics Depts. State University of New York Buffalo, NY 14260	Dr. Z.H. Kafafi Optical Sci. Div., Code 6551 Naval Research Laboratory Washington, DC 20375-5000	Dr. G.B. Stringfellow Mats. Science & Engineering University of Utah Salt Lake City, UT 84112	Dr. John T. Yates Chemistry Dept. University of Pittsburgh Pittsburgh, PA 15260	Dr. Richard W. Drisko Naval Civil Engineering Lab Code L-52 Port Hueneme, CA 93043
Dr. S. Brackenstein Department of Chemistry State University of NY Buffalo, NY 14214	Dr. Arnold Green Quantum Surface Dynamics Br. Naval Weapons Ctr., Code 3817 China Lake, CA 93555	Dr. George H. Morrison Chemistry Dept. Cornell University Ithaca, NY 14853	Dr. Galen D. Sucky Chemistry Dept. University of California Santa Barbara, CA 93106	Dr. E. Yeager Chemistry Dept. Case Western Reserve Univ. Cleveland, OH 41106	Defense Tech. Information Ctr. Building 5 Cameron Station Alexandria, VA 22314
Dr. J. Beiler Naval Research Laboratory Code 6115 Washington, DC 20375-5000	Dr. R. Hamers IBM Watson Research Center PO Box 218 Yorktown Heights, NY 10598	Dr. Daniel M. Neumark Chemistry Department University of California Berkeley, CA 94720	Dr. H. Tachikawa Chemistry Dept. Jackson State University Jackson, MI 39217	David Taylor Research Center Attn: Dr. Eugene C. Fischer Applied Chemistry Division Annapolis, MD 21402-5067	
Dr. R.P.H. Chang Mats. Science & Engineering Northwestern University Evanston, IL 60208	Dr. Paul K. Hansma Department of Physics University of California Santa Barbara, CA 93106	Dr. D. Ramaker Chemistry Dept. George Washington Univ. Washington, DC 20052	Dr. W. Unertl Surface Science & Technol. Lab University of Maine Orono, ME 04469	Dr. James S. Murlay Chemistry Div., Code 6100 Naval Research Laboratory Washington, DC 20375-5000	
Dr. Paul A. Christian Adv. Chem. Technol., Fed. Systems Eastman Kodak Company Rochester, NY 14650-2156	Dr. C.B. Harris Chemistry Dept. University of California Berkeley, CA 94720	Dr. R. Reeves Chemistry Dept. Rensselaer Polytech. Inst. Troy, NY 12181	Dr. R.P. Van Doyne Chemistry Dept. Northwestern University Evanston, IL 60201	Dr. David Nelson Office of Naval Res. Code 413 800 N. Quincy Street Arlington, VA 22217-5000	
Dr. Richard Colton Code 6170 Naval Research Laboratory Washington, DC 20375-5000	Dr. J.C. Hemminger Chemistry Dept. University of California Irvine, CA 92717	Dr. A. Reisman Microelectronics Center Research Triangle Park No. Carolina, 27709	Dr. David M. Walba Chemistry Department University of Colorado Boulder, CO 80309-0215	Dr. Ronald L. Atkins Chemistry Div., Code 385 Naval Weapons Center China Lake, CA 93555-6001	
Dr. J.E. Demuth IBM Watson Research Center PO Box 218 Yorktown Heights, NY 10598	Dr. Roald Hoffmann Chemistry Dept. Cornell University Ithaca, NY 14853	Dr. G. Ruboff IBM Watson Research Ctr. PO Box 218 Yorktown Hgts, NY 10598	Dr. J.H. Weaver Chemical Engrg. & Mats. Sci. University of Minnesota Minneapolis, MN 55455	Dr. Bernadette Eichinger Naval Ships Systems Engrg. Station Phila. Naval Base, Code 053 Philadelphia, PA 19112	
Dr. F.J. DiSalvo Department of Chemistry Cornell University Ithaca, NY 14853	Dr. L. Interrante Chemistry Dept. Rensselaer Polytech. Inst. Troy, NY 12181	Dr. Richard J. Seytally Chemistry Department University of California Berkeley, CA 94720	Dr. B.R. Weiner Department of Chemistry University of Puerto Rico Rio Piedras, PR 00931	David Taylor Research Station Attn: Dr. H. H. Singerman Code 283 Annapolis, MD 21402-5067	
Dr. A.B. Ellis Department of Chemistry University of Wisconsin Madison, WI 53706	Dr. E.A. Irene Chemistry Dept. Univ. of North Carolina Chapel Hill, NC 27514	Dr. Robert W. Shaw US Army Research Office Box 12211 Res. Triangle Park, NC 27709	Dr. Robert L. Whetten Chemistry Department University of California Los Angeles, CA 90024	Dr. Sachio Yamamoto Naval Ocean Systems Center Code 52 San Diego, CA 91232	
Dr. M.A. El-Sayed Chemistry Department University of California Los Angeles, 90024-1569	Dr. D.E. Irish Department of Chemistry University of Waterloo ONT N2L 3G1, Canada	Dr. S. Sibener James Franck Institute University of Chicago Chicago, IL 60637	Dr. R. Stanley Williams Dept. of Chemistry University of California Los Angeles, CA 90024	Carlota Leafroy Office of Naval Research 1030 E. Green Street Pasadena, CA 91106	